


# OptiTune 15

## OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	13 %	13 %
Visible Light Reflected (Int)	25 %	24 %
Visible Light Reflected (Ext)	56 %	56 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	51 %	46 %
Total Solar Energy Transmitted	12 %	11%
Total Solar Energy Absorbed	37 %	43 %
Emissivity (Room Side)	0.76	0.76
Glare Reduction	85 %	85 %
Shading Coefficient	0.26	0.37
Solar Heat Gain Coeff. (G-Value)	0.22	0.32
U-Value Winter (IP)	1.00	0.47
U-Value Winter (SI)	5.68	2.67
Luminous Efficacy	0.50	0.34
Total Solar Energy Rejected	78 %	68 %

R070R1W - OptiTune 15 Water Activated Adhesive



Ed-C DS No 1162 August 2011