

Solar Bronze 20

OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	17 %	16 %
Visible Light Reflected (Int)	45 %	45 %
Visible Light Reflected (Ext)	40 %	43 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	53 %	47 %
Total Solar Energy Transmitted	9 %	8 %
Total Solar Energy Absorbed	38 %	45 %
Emissivity (Room Side)	0.69	0.69
Glare Reduction	81 %	81 %
Shading Coefficient	0.23	0.35
Solar Heat Gain Coeff. (G-Value)	0.19	0.30
U-Value Winter (IP)	0.96	0.46
U-Value Winter (SI)	5.45	2.61
Luminous Efficacy	0.74	0.45
Total Solar Energy Rejected	81 %	70 %

R069B6W - Solar Bronze 20 Water Activated Adhesive

R069B6S - Solar Bronze 20 Pressure Sensitive Adhesive

